

DynoFlex

DESCRIPTION: Safecoat DynoFlex is a unique, water based, low odor elastomeric sealer formulated in a paste-like compound for sealing seams, joints and cracks in new and old heating and air conditioning ducts, and for repairing metal roofs and asphalt shingles. Safecoat DynoFlex is highly resistant to harsh weather and temperature changes. It remains flexible and prevents leaks even after exposure to the elements or contraction due to weather. Safecoat DynoFlex is resistant to gasoline, oil, grease, fungi, acids, alkalines and flame spread. It is also a superb sound deadener.

PRODUCT NUMBER AND CONTAINER SIZE: 51173 (quart) and 51373 (five gallon).

USE ON: Safecoat DynoFlex is recommended for new and old heating and air conditioning ducts, metal roof cracks, damaged asphalt shingles, mobile home roofs and similar areas.

ADVANTAGES / SIGNIFICANT BENEFITS:

- Effective, easy to use.
- Non-offensive to installer and occupant.
- When used in conjunction with **SafeChoice Super Clean** and **SafeChoice X-158**, DynoFlex is a full system for sealing, cleaning and maintaining all heating and air conditioning ducts.
- Safely used by and for the chemically sensitive.
- Very low VOC content, meets or exceeds all federal and state air quality regulations, including California.

APPLICATION: Always have adequate ventilation. All areas to be coated should be clean and dry. Remove all oil, dirt, dust, rust and loose residue. When possible clean with a not toxic, biodegradable and odorless cleaner like **SafeChoice Super Clean**. Old asphalt shingles should be power washed prior to treatment. Allow all surfaces to dry completely before applying DynoFlex. Apply DynoFlex at 15 mils wet directly from the container without dilution. Use a brush, squeegee-type applicator or trowel and smooth evenly to produce a uniform and seamless coat. Two coats provide additional protection. *Note: these instructions are intended to be general only and not exhaustive. The applicator should determine which preparation and techniques are best suited to the specific surface.*

COVERAGE: One gallon of Safecoat DynoFlex covers approximately 100 square feet at 15 mils thickness.

CLEAN-UP: Clean tools and equipment while they are still wet with a solution of **SafeChoice Super Clean** and warm water.

DRYING/CURING TIME: To touch within 2 hours. Cures hard in 24 hours.

LIMITATIONS: Unlike conventional sealers, Safecoat sealers are made without formaldehyde preservatives or toxic mildewcides or fungicides. Do not contaminate. Store in airtight containers. Do not use when indoor or surface temperature is below 55°F. Avoid application in direct hot sun, which may cause premature dry-out. If product has thickened in container add a small amount of water and stir to return product to original paste consistency. Keep from freezing.

HEALTH PRECAUTIONS: As with all coatings and stains, keep container tightly closed and out of the reach of children. Do not take internally. Always use adequate ventilation. *If you are chemically sensitive, always test for personal tolerance.*

LIMITED LIABILITY: Safecoat® products are guaranteed not to be defective when properly applied. Liability express or implied is limited to replacement of product or refund of purchase price and does not include liability for labor costs or consequential damages. Variable factors out of manufacturer's control, such as environmental conditions, application techniques, and surface conditions are critical to results obtained. Users are expected to exercise reasonable care to determine suitability of the product for each application. This limited warranty may not be modified or extended by manufacturer's representatives, distributors or dealers of AFM products. **We particularly recommend that users always test in small inconspicuous areas before application to the entire surface.**