Safecoat Naturals Flat

Installation Guidelines

PRODUCT NUMBER AND CONTAINER SIZE
47211 Qt/47111 Gal
47311 5g pail

WATER BASED/COVERAGE: One gallon covers approximately 350-400 SF.

USE ON:

Previously painted walls, ceilings, wood and wood trim, fully cured plaster (below 10 pH), stucco and masonry.

LIMITATIONS:

Safecoat paints are made without formaldehyde preservatives. Do not contaminate. Store in air-tight containers. Do not use when indoor temperature is below 55 degrees F. Do not freeze. **Thick application, high humidity or conditions other than normal will cause Safecoat to dry and cure more slowly.**

SURFACE PREPARATION:

Clean surfaces of dirt, grease, mildew and oil. Knot holes and water stains should be spot primed with Safecoat KnotSealer.
Surfaces painted with shiny coatings should be sanded to promote adhesion.
(all gloss must be removed).
Wet sanding is recommended.
Surface should be completely dry before application. **Always spot test for adhesion over prior coatings.**

APPLICATION:

Before using, stir Safecoat Naturals Flat well, then apply as is stirring occasionally during use.

Apply with a brush, roller or airless sprayer.

Spraying, reduce with up to 1/2 pint of water per gallon. Use a painter's mask when spraying. (Note: highpile heights will add additional texture.) Airless sprayers should have a 17/1000 to 21/1000 tip (reversible type is best). Only a 30 mesh high pressure filter should be used. Use a painter's mask when spraying. For full coverage application, overlap preceding application with 1/4 to 1/2 the fan width at a distance of 18" from surface.

CLEAN-UP:

Clean tools and equipment while they are still wet with a warm soapy water solution.

DRYING/CURING TIME:

Under normal conditions, Safecoat® Naturals Flat can be recoated after 4 hours. For best results, wait at least 8 hours before recoating. Normal conditions include: a dry surface, access to fresh air flow, moderate humidity, and temperatures above 55°F. Thick application, high humidity, or conditions other than normal will cause paint to dry and cure more slowly. Drying and curing time can be accelerated by moving fresh air over the painted surface, but recoating before the time period noted above is not recommended and temperatures above 55 degrees F.

HEALTH PRECAUTIONS:

As with all coatings and sealers, keep container tightly closed and out of the reach of children. Do not take internally. Keep from freezing. Always use adequate ventilation.

PHYSICAL DATA

Physical Description:	Low odor, mildly alkaline, white
% Volatile by Volume:	61.83%
Solubility in Water:	Dilutable
% Volatile by Weight:	48.25 %
VOC Material:	22 g/l
VOC Material less H20:	49 g/l

HAP's (Hazardous Air Pollutants) zero

If you are chemically sensitive, always test for personal tolerance.

Test samples available here: www.thegreendesigncenter.com/product/afm-2oz-samples/

LIMITED LIABILITY: Liability, whether express or implied, is limited solely to replacement of product shown to be defective when applied in accordance with instructions and shall under no circumstances include liability for labor costs or consequential damages. It is the user's responsibility to determine the suitability and safety of the product for its intended use. This limited warranty may not be modified or extended by manufacturer's representatives, distributors, or dealers of AFM products. We particularly recommend that users always test in small inconspicuous areas before application to the entire surface.

American Formulating and Manufacturing 3251 Third Ave., San Diego, CA 92103 www.afmsafecoat.com.